

Sub
D1

2. The method as defined in claim 1, wherein said metal is nickel and the corrosion resisting material forming the component is chromium constituting between 48% and 52% of weight of the alloy as the high content thereof.

3. The method as defined in claim 2, further including: selection of nitrogen as the inert gas; pressurizing said inert gas and directing jets thereof into said molten alloy stream for effecting said atomization and deposit onto the surface.

5. In a method of casting a ductile alloy having a base metal by heating thereof to produce a molten stream that is atomized into a spray of droplets directed onto a moving substrate surface; the improvement residing in: selecting a corrosion resisting material as a component of the alloy undergoing said heating; exclusively limiting said alloy to the base metal and the corrosion resisting material; and utilizing an inert cover gas to atomize the molten stream into said spray of droplets for deposit onto said surface to increase in strength the ductile alloy.

B2
Sub
D2

6. The method as defined in claim 5, wherein said base metal is nickel, the corrosion resisting material is chromium and the inert cover gas is nitrogen.

7. In a method of producing an alloy formed exclusively from a base metal and a corrosion resisting component deposited onto a moving substrate surface, the improvement residing in: limiting the alloy exclusively to said base metal and the corrosion-resisting component; and forming the alloy by spray casting under exposure to an inert cover gas for said deposit onto said surface to thereby exhibit high strength while maintaining ductility.

- B2 sub 03
8. The method as defined in claim 7, wherein said base metal is nickel, said corrosion-resisting component is chromium and said inert cover gas is nitrogen.